

# **Certificate of Conformance** to Requirements for Welding Electrode

Product Type: FABCO RXR

Classification: **E70T-1C**; **E70T-9C** 

Specifications: AWS A5.20/A5.20M; ASME SFA 5.20

 Diameter Tested:
 .045"; 3/32"

 Date Tested:
 6/5/2020

 Date Generated:
 8/10/2020

This is to certify that the product named above and supplied on the referenced order number is of the same classification, manufacturing process, and material requirements as the material which was used for the test that was concluded on the date shown, the results of which are shown below. All tests required by the specifications shown for classification were performed at that time and the material tested met all requirements. It was manufactured and supplied by the Quality System Program of Hobart Brothers, which meets the requirements of ISO 9001, ANSI/AWS A5.01, and other specification and Military requirements, as applicable. This document supplies actual test results of non-specific inspection in conformance with the requirements of EN 10204, type 2.2 certification.

## THE STEEL USED IN THIS LOT OF MATERIAL WAS MELTED AND MANUFACTURED IN THE U.S.A.

### **Test Settings**

Shielding Medium	Amps / Polarity	Volts	WFS in/min(m/min)	ESO in(mm)	Preheat F(C)	Interpass F(C)	Travel Speed in/min(cm/min)					
C1 (100% CO2)	250 / DCEP	28	420 (10.7)	3/4 (19)	()	()	10 (25.4)					
C1 (100% CO2)	420 / DCEP	32	165 (4.2)	1 (25)	Room Temp	300(149)	12 (30.5)					
Mechanical Properties - Tensile												

Shielding Medium	Ref. No.	Testing Conditions	Ult. Tensile Strength psi (MPa)	Yield Strength psi (MPa)	Elong.% in 2"
C1 (100% CO2)	PD9661	Aged 48 Hrs 220F	82,000 ( 565 )	72,000 ( 496 )	27
C1 (100% CO2)	pd9860	Aged 48 Hrs 220F	91,000 ( 629 )	79,000 ( 543 )	26

#### **Mechanical Properties - Impact**

Shielding Medium	Ref. No.	Testing Conditions	Temp. F (C)	Individuals ft.lb.(J)	Avg. ft.lb.(J)	Туре
C1 (100% CO2)	PD9661	As Welded	-20 (-29)	47,52,58 (64,70,79)	52 ( 71 )	Charpy-V-Notch
C1 (100% CO2)	PD9661	As Welded	0 (-18)	62,67,61 (84,91,83)	63 ( 86 )	Charpy-V-Notch
C1 (100% CO2)	PD9860	As Welded	0 (-18)	58,56,55 (79,76,75)	56 ( 76 )	Charpy-V-Notch
C1 (100% CO2)	PD9860	As Welded	-20 (-29)	44,51,45 (60,69,61)	47 ( 63 )	Charpy-V-Notch

Ref.No. Radiographic Inspection		Fillet Weld Test								
PD9661	Conforms	Horizontal :	Conforms	Overhead :		Vertical :				
PD9860	Conforms	Horizontal :	Conforms	Overhead :		Vertical :				

## **Chemical Analysis**

Shielding Medium / Ref. No	С	Mn	Р	S	Si	Cu	Cr	V	Ni	Мо	ΑI	Ti	Nb	Со	В	W	Sn	Fe	Sb	N	Mg	Zn	Ве	Sb	As
C1 (100% CO2) / CD59829	0.06	1.68	0.008	0.007	0.77	0.06	0.04	0.02	0.02	0.01		0.02	0.01		0.0011										
C1 (100% CO2) / PD9661	0.05	1.68	0.008	0.008	0.62	0.02	0.04	0.02	0.01	0.01		0.03	0.01		0.0008										

Dave Thomas, Quality Assurance Rep.

Certification and Limited Warranty - Data for the above supplied product are those obtained when welded and tested in accordance with the above specification. All tests for the above classification were satisfied. Other tests and procedures may produce different results.